

### Description

For the lubrication of pneumatic equipment via compressed air service units or oil-fog lubricators.

### Properties

- lasting corrosion protection
- excellent wear resistance
- excellent low temperature behavior
- excellent resistance to aging

### Technical data

SAE class (engine oils)	10W SAE J300
Density at 15 °C	0,86 g/cm <sup>3</sup> DIN 51757
Viscosity at 40 °C	38 mm <sup>2</sup> /s ASTM D 7042-04
Viscosity at 100 °C	6,6 mm <sup>2</sup> /s ASTM D 7042-04
Viscosity at -30 °C (MRV)	< 60000 mPas ASTM D4684
Viscosity at -25 °C (CCS)	≤ 7000 mPas ASTM D5293
Viscosity index	130 DIN ISO 2909
Pour point	-39 °C DIN ISO 3016
Evaporation loss (Noack)	10 % CEC-L-40-A-93
Flash point	220 °C DIN ISO 2592
Total base number	10,3 mg KOH/g DIN ISO 3771
Sulfate ash	1,2 g/100g DIN 51575
Color number (ASTM)	3,5 DIN ISO 2049



### Available pack sizes

50 ml Can plastic 7841  
D

**Our information is based on thorough research and may be considered reliable, although not legally binding.**

### Areas of application

For lubrication and extension of the service life of the respective pneumatic tools used in compressed air service units or oil-fog lubricators.

### Application

Fill oil for pneumatic equipment in the compressed air service unit or in the oil-fog lubricator up to the max. marking on the inspection glass. The manufacturer's filling instructions must be observed!

### Available pack sizes