

## LM 203 MoS2 Anti-Friction Lacquer

### Description

Rapid drying, resin-bound MoS2 anti-friction lacquer dispersed in solvent. Produces an adherent film of dry lubricant with low friction values.

### Properties

- extremely fast drying properties
- extremely high UV resistance
- friction and wear reducing
- high bond strength
- resistant to mineral oils
- good corrosion protection
- outstanding emergency-running properties
- dries at room temperature

### Technical data

Color / appearance	black/grey film, matt
Base	MoS2
Binder	resin
Operating temperature range	up to + 450 °C
Coating thickness	15 - 20 µm
Odor	characteristic
Form	aerosol, liquid

### Areas of application

Used for pre-treatment of drive elements under heavy load such as gearwheels, racks, profiled shafts and joints. For lubrication during the assembly of press fittings and for treatment of work pieces and tools during metal forming and metal processing.

### Comment

**Note:** After use, clear aerosol can spray nozzle (hold can with spray head upside down) by spraying until only pure propellant emerges.

### Application

Surfaces to be coated must be bare metal, free from grease and dry. Lightly roughening the surface by sand blasting, grinding with emery, pickling or phosphating will produce the optimum service life for the film. Application from aerosol can (recommended layer thickness 15 – 20 µm). Drying time depends on the temperature.

### Available pack sizes

300 ml Can aerosol 23146  
DE-EN

**Our information is based on thorough research and may be considered reliable, although not legally binding.**

