

Ceramic Paste

Description

Metal-free universal paste for the most demanding applications. With a partially synthetic base oil, sophisticated additive technology and state-of-the-art solid lubricants from the area of high-tech ceramics.

Properties

- resistant to certain organic acids and alkalis
- prevents stick slip
- good water resistance
- prevents seizing and cold welding
- does not attack common sealing materials
- prevents brake noise
- highest load-carrying capacity
- non-toxic

Technical data

Color / appearance	weiß / white
Base	Synthese-/Mineralöl / synthetic/mineral oil
Thickener	anorganische Dickungsmittel und weiße Festschmierstoffe / inorganic thickening agents and white solid lubricants
Density	1,42 g/cm ³
Operating temperature range	-40 bis 1400 °C als Trennpaste / as a separating paste
Unworked penetration	ca. 340
Base oil viscosity 40°C	ca.100 mm ² /s
Four-ball tester material load/weld force	3800/4000 N DIN 51 350,4
Friction numbers - thread	0,10 DIN 946
Pressfit test (no stick slip)	0,08 LFW-4
SRV (cylinder/plate; 450 N, 1,000 µm, 50 Hz, 2 h) - friction number	0,10-0,13 µm Reibungszahl / coefficient of friction

Areas of application

For lubrication of all kinds of high-load sliding surfaces. Especially for low slide speeds and oscillating movements. Also for screw, plug-in and bayonet connectors made from steel and non-ferrous metals. For separation of components subject to heat stress, such as combustion engines, turbines and motor vehicle brake systems. As corrosion protection for bolts, pins,



studs, flanges, spindles and seatings in refineries, steel and cement works as well as shipping and agricultural engineering.

Application

Before treating, parts must be clean and free from residues, dirt and moisture. Apply to cleaned surfaces using a paint brush, brush or lint-free cloth. Amount depends on area of use and application.

Available pack sizes

50 g Tube plastic	3418 D-GB-E
250 g Brush-in-cap can sheet metal	3420 D-GB-I-E-P
1 kg Can sheet metal	3413 D-GB-I-E-P

Our information is based on thorough research and may be considered reliable, although not legally binding.