

LM 301 A Contact-Oil

Properties

- excellent penetration action
- compatible with plastics
- good lubrication at high load
- wide operating temperature range
- silicone-free
- good electronic properties
- good corrosion protection
- high resistance to aging



Technical data

Color / appearance	gelb
Base	Syntheseöl
Viscosity at 104 °F	224 mm ² /s nach Abdampfung
Viscosity at 212°F	37,8 mm ² /s nach Abdampfung
Viscosity at -4 °F	30000 mm ² /s nach Abdampfung
Density at 68 °F	0,993 g/cm ³ DIN 51757
Viscosity index	221 DIN ISO 2909
Pour point	-29 °F DIN ISO 3016
Flash point	183 °F DIN ISO 2592
Evaporation loss	9 Gew.-% DIN 51 581
Neutralization number	0,04 mg KOH/g DIN 51 809
Water content	< 0,25 mg KOH/g DIN ISO 3733
Specific electrical volume resistance at 68 °F	3,8 • 10 ¹⁰ Ω · cm

Available pack sizes

150 ml Can aerosol 3236
D-GB-E-F-NL

**Our information is based on thorough research
and may be considered reliable, although not
legally binding.**