

Product information

Meguin Wälzlagerfett LP2



Characteristic data

Saponification type	Lithiumseife
Brief description	KP2K-30 DIN 51502
NLGI number	2 DIN 51818
Worked penetration	265-295 1/10 mm DIN ISO 2137
Dropping point	> 190 °C DIN ISO 2176
Oil separation after 7 days at 104 °F	5,9 % DIN 51817
Oil separation after 18 hours at 104 °F	1,8 % DIN 51817
Flow pressure at -22 °F	<1400 mbar DIN 51805
Emcor corrosion class	0/0 DIN 51802
Copper corrosion after 24 hours at 212 °F	1 b DIN 51811
Behavior in the presence of water	1-90 DIN 51807 Teil 1
Four-ball tester material load/weld force	2200/2400 N DIN 51350 Teil 4
Four-ball tester wear/indentation diameter	0,5 mm DIN 51350 Teil 5
Base oil	mineral
Viscosity at 104 °F	160 mm ² /s ASTM D 7042-04
Flash point	242 °F DIN ISO 2592
Pour point	-24 °F DIN ISO 3016

Available pack sizes

5 kg Bucket plastic	4766 D-GB
15 kg Bucket plastic	8427 D-GB
25 kg Bucket plastic	4768 D-GB
50 kg Bucket sheet metal	4776 D-GB
180 kg Drum sheet metal	6446 D-GB
400 g Cartridge plastic	4769 D-GB-F-HR-RUS-GR
400 g Lube-Shuttle	9029 D-GB-F-HR-RUS-GR

