

Hohlraumversiegelung hellbraun (Spray)**Properties**

- good heat resistance
- reduces fretting corrosion
- penetrates and drives out moisture
- outstanding corrosion protection
- excellent penetration action
- short follow-up time

Technical data

Base	wax
Color / appearance	brown
Flash point	<0 °C
	Wirkstoff
Odor	characteristic
Skin formation time at 68 °F/65 % relative humidity	ca. 90 min
Through-drying	ca. 180 min
Consumption coat thickness at 100 µm wet	ca. 9 m ² /l
Consumption coat thickness at 200 µm wet	± 0,2 l/m ²
Corrosion resistance salt-spray test	>480 h
Shelf life in original sealed container	24 Monate
Recommended storage temperature	-20 °F

Available pack sizes

500 ml Can aerosol 6107
D-GB-F-I-E-NL-P

Our information is based on thorough research and may be considered reliable, although not legally binding.

