Product information
Liquifast 1402

PI 28/07/30/2025

Description
1-component, cold-application, moisture-curing adhesive for direct glazing of vehicle windows in the case of repairs. Liquifast 1402 was tested in a crash by the TÜV testing agency. Characterized by its fast curing properties and excellent rigidity. Vehicles whose windows were bonded using Liquifast 1402 are ready to be driven again after just 1.5 hours (with or without driver airbag) or 3 hours (with front passenger airbag) of drying time according to general test conditions.

Properties
- single-component
- high viscosity
- fast bonding properties
- proven OEM quality
- cold working
- TÜV tested
- cured by moisture in the air

Technical data

Base	polyurethane pre-polymers
Color / appearance	black
Odor	characteristic
Extrusion viscosity	pastös,pumpbar GM001.0
Density at 20 °C	1,2 g/cm³
Flash point	>100 °C
Dry content	>98 % GM 0,42.0
Rigidity	good, non-flowing
Processing temperature	ideally 10°C-35°C
Processing time	max. 10 min. at 23 °C/50 % r.h. in association with adhesion promoter
Skin formation time at 23 °C/50 % relative humidity	ca. 10 min GM 006.0
Curing rate at 23 °C / 50 % rh	approx. 4.5 mm within the first 48h at 23°C/50% GM 007.0
Combined tension and shear resistance	> 5 MPa GM 021.0
Tensile strength	> 6 MPa DIN 53 504
Ultimate elongation	ca. 450 % DIN 53 504
Resilience	ca. 99 % EN 27 389



Technical data

Hardness, Shore A	45-60 DIN 53 505
Shelf life with original closed container	18 months
Recommended storage temperature	0 - 35 °C

Areas of application
Bonding of windshields, rear windows and side windows to vehicle bodies (cars, trucks, the drivers' cabins of tractors/forklift trucks, and special vehicles). Bonding of side windows made from single pane and insulation glass in bus and train car construction.

Comment
Recommendations for use are provided in the brochure supplied.

Application
1. Cleaner
The surfaces to be bonded must be dry, free from oil, dust, grease and other dirt residues. The glass surface or the ceramic coating is cleaned with Liquiclean or Cleaner and Thinner, part no. 6130, and finally with Window Cleaner Foam, part no. 1512, as are the bodywork flange or newly painted car-body components. We recommend also cleaning the remaining adhesive beading that has been trimmed back with Liquiclean or Cleaner and Thinner. Before applying the sealant or bonding the window, the cleaned bonding surface must be completely dry.
2. Priming/activation of pre-coated windows
Active Primer is required for adhesive pre-treating during window bonding. The Active Primer is included in the scope of delivery of the Window Repair Kit as a 10 ml stick. Shake Active Primer well for at least 45 seconds before use. Active Primer can be applied universally in the bonding area thinly and evenly (approx. 0.05 mm wet-film thickness) on the cleaned glass surface or ceramic screen printing, on the clean paint surface of newly painted car-body components, on remaining adhesive beadings that have been trimmed back and pre-coated windows (PUR and RIM coatings). The primed surface must be allowed to air off for about 15 minutes before applying the

LIQUI MOLY GmbH
Jerg-Wieland-Str. 4
89081 Ulm-Lehr

Phone: +49 (0)731/1420-0
Fax: +49 (0)731/1420-82
e-mail: info@liqui-moly.de

Technical hotline: +49 (0)731/1420-871
www.liqui-moly.com

Product information

PI 28/07/30/2025

Liquifast 1402

Windshield Adhesive.
If the remaining adhesive beading was trimmed back more than 6 hours ago, pre-treatment with Active Primer is mandatory.

Available pack sizes

310 ml Cartridge aluminum	6136 D-GB-P-I

Our information is based on thorough research and may be considered reliable, although not legally binding.

LIQUI MOLY GmbH
Jerg-Wieland-Str. 4
89081 Ulm-Lehr

Phone: +49 (0)731/1420-0
Fax: +49 (0)731/1420-82
e-mail: info@liqui-moly.de

Technical hotline: +49 (0)731/1420-871
www.liqui-moly.com