Product information

PI 14/06/12/2025

Liquimate 8300 Seam Sealant black



Description

High-grade, 1-component, MS polymer-based, sprayable seam sealant. Free of isocyanate and silicone. Resistant to UV and mineral oils. With most commercially available paints, can be painted over wet-on-wet immediately (max. up to 2 hours).

Properties

- fast-drying
- permanently elastic after curing
- easy to use
- odorless
- resistant to mineral oils
- can be painted over wet-in-wet
- waterproof
- free of isocyanate
- can be used without primer
- silicone-free
- can be applied as a spray or with a brush
- outstanding rigidity
- broad adhesive spectrum
- high resistance to aging
- Sealing compound and sprayable seam sealant
- professional repairs
- high adhesive strength

Technical data

Base	MS-Polymer
Form	pastelike
Color / appearance	black
Odor	petrol-like
Density at 20 °C	1,38 g/cm³
Curing rate at 23 °C / 50 % rh	~ 3 mm/24 h DIN 50 015
Skin formation time at 23 °C/50 % relative humidity	20 min DIN 50 015
Elongation at break	250 %
Hardness, Shore A	47 DIN 53 505
Curing system	cured by moisture in the air
Thermal stability after curing	-120 °C
Tensile strength	2,1 N/mm²
Tear growth resistance	5 N/mm DIN 53515
Recommended storage temperature	⩽ 25 °C
Shelf life in original sealed container	18 months

Areas of application

For sealing seams during repairs to restore to original factory condition. Areas of application include the engine compartment, trunk and wheel housings.

Application

Surfaces must be clean and free of grease. Can be painted over after application of the material with solvent- and water-based paints. It is recommended that you check the adhesion and compatibility with plastics and paints for the specific object.

Available pack sizes

310 ml Cartridge plastic	6151 DE-EN-ES-FR-IT-NL-PT

Our information is based on thorough research and may be considered reliable, although not legally binding.

LIQUI MOLY GmbH
Jerg-Wieland-Str. 4
89081 Ulm-Lehr

Phone: +49 (0)731/1420-0
Fax: +49 (0)731/1420-82
e-mail: info@liqui-moly.de

Technical hotline: +49 (0)731/1420-871
www.liqui-moly.com