

Liquimate Kraftkleber 8050 MS**Properties**

- can be used without primer
- extremely high UV resistance
- can be painted over wet-in-wet
- outstanding resistance to salt water
- after drying, very easy to grind
- does not contain solvent, isocyanate or silicones
- outstandingly adherent

**Technical data**

Color / appearance	black
Base	MS Polymer
Thermal stability	-40 to +120, short term up to +180 °C
Processing temperature	+5 to +35 °C
Chemical resistance	against water and aliphatic solvents, dilute inorganic acids and alkalis, oil and greases
missing translation	aromatic solvents, concentrated acids and chlorinated hydrocarbons
Shrinkage	< 3 %
Form	paste-like
Odor	mild
Hardness, Shore A	~ 58 DIN 53505
Density at 68 °F	1,45 g/ml
Tear propagation	~ 16 N/mm DIN 53515/ISO 34
Curing system	cured by moisture in the air
Ultimate elongation	~ 225 % DIN 53504/ISO 34
Skin formation time at 68 °F/65 % relative humidity	< 15 min
Curing rate at 68 °F / 65 % rh	24h
Combined tension and shear resistance	~ 2,5 - ~3,3 MPa
Shelf life in original sealed container	18 Monate
Recommended storage temperature	5 - 35 °C

Our information is based on thorough research and may be considered reliable, although not legally binding.

Available pack sizes

290 ml Cartridge plastic	6165 D-GB-F-I-E-NL-P
--------------------------	-------------------------