Product information

PI 38/03/27/2024

Liquimate 2-Component Power Adhesive

methyl

< 20 °C

Phone: +49 (0)731/1420-0 Fax: +49 (0)731/1420-82 e-mail: info@liqui-moly.de



Description

High-strength, fast-curing 2-component methyl acrylate adhesive. For permanent high-performance bonding of steel, aluminum, metals, heat-formable plastics, composite materials ABS, acrylics, PVC, GFRP, PC, PET, PU, etc. to themselves and to each other. Extremely impact and peel resistant and can be processed as required. Stable in the presence of gasoline, oil, mild acids and alkalis.

Properties

- outstanding shear resistance
- cures at room temperature
- resistant to water-based acids
- excellent resistance to weathering
- good water resistance
- resistant to gasoline and oil
- excellent peel strength and impact resistance

Technical data

Base

2400	methacrylate
Color / appearance	opaque
Density at 20 °C	0,95 (B) g/cm³
Viscosity at 20 °C	150.000 bis/to 200.000 (B) mPas
Flash point	11 °C
Mixing ratio	01:01
Processing time	5-7 min
Fixing time	10-12 min
Thermal stability	-55°C to +120°C
Elongation at break	2,4 %
Initial strength	1 h
Shrinkage	5 %
Shore D hardness	75
Gap filling capability	1-10 mm
Shelf life in original sealed container	12 months

Areas of application

temperature

Recommended storage

Universal adhesive for body and vehicle manufacture (e.g. bumper, radiator, lights, handles, console parts, spoiler, phone and speaker attachment). Replacement mixer (mixer tip with thread, part no. 6029).

Comment

Attention: To clean, use only LIQUI MOLY Cleaner and Thinner, Part no. 6130. Do not use cellulose lacquer



thinners or alcohol!

Application

For the best possible adhesion result, clean and degrease surfaces with LIQUI MOLY Cleaner and Thinner (Part no. 6130). Some surfaces must be roughened. Press the adhesive out of the double syringe and mix both components well with an applicator (automatic mixing when using the mixer nozzle). Apply the adhesive and join the parts (max. processing time 5 – 7 minutes). Firm to the touch after approx. 1 h and hardened through after 24 h. Curing time depends on room temperature. Do not use the adhesive below 0 °C. After use, close the container with the cap. Store in a cool, dry place.

Available pack sizes

25 ml Blister 6179 D-GB-E

Our information is based on thorough research and may be considered reliable, although not legally binding.