Product information
Active Primer

PI 25/02/18/2026

Description
All-in-one product with additional functions for glazing using polyurethanes (PUR). Used as a bonding agent for glass, ceramic screen printing and paints for use with all PUR adhesive and sealing compounds. At the same time, Active Primer is a PUR activator for residual PUR beading, PUR base coats and RIM coatings. The product contains less than 0.1 wt. % of isocyanates and is thus not subject to any training obligation under the REACH Regulation.



Properties
- extremely high UV resistance
- good corrosion protection
- accelerated adhesion build-up
- bonding agent for residual PUR beading
- satisfies OEM requirements
- bonding agent for glass and ceramic screen printing
- bonding agent RIM coatings
- bonding agent for PUR base coats
- bonding agent for paints
- NCO-konform

Technical data

Color / appearance	black
Form	liquid
Flash point	-4 °C
Odor	characteristic
Density at 20 °C	0,98 g/cm³
Shelf life in original sealed container	12 months
Flash-off period	at least 10 Minutes (at 23°C/50% relative humidity)

Areas of application
For adhesion and for UV protection of direct-glazing sealants, as well as a bonding agent for PUR base coats (e.g. Volkswagen), residual PUR beading and RIM coatings (e.g. Opel).

Application
Before application, make sure that the bonding surface is clean and free of grease. We recommend cleaning with Liquiclean or Cleaner and Thinner in the bonding area of the bodywork flange as well as the windshield and for the ceramic screen printing. Additional cleaning with Windshield Cleaner Foam is required to remove all contaminants. Shake the primer well before use (at least 45 s after the steel balls have worked free in the case of aluminum cans). With the 10 ml stick, after shaking immediately screw on the sponge head and apply/process.

Attention: Product is moisture-sensitive! Remaining contents of sticks and 30 ml containers are to be disposed of after being used once. 100 ml containers which have been opened must be closed immediately after extracting contents and used within 3 days.

Available pack sizes

10 ml Stick aluminum	6180 DE
30 ml Bottle aluminum	6181 DE-FR
100 ml Bottle aluminum	6182 DE-FR-IT

Our information is based on thorough research and may be considered reliable, although not legally binding.

LIQUI MOLY GmbH
Jerg-Wieland-Str. 4
89081 Ulm-Lehr

Phone: +49 (0)731/1420-0
Fax: +49 (0)731/1420-82
e-mail: info@liqui-moly.de

Technical hotline: +49 (0)731/1420-871
www.liqui-moly.com