Product information

PI 18/09/11/2025

Glass Sealing Compound; can be dapped off

Description

Spotting Glazing Sealant is a permanently adhesive, non-hardening, polyisobutylene-based sealing compound which can be applied by spotting but cannot be painted over. This product is mainly used in the car industry for sealing rubber mounted front and rear windshields and side windows between the rubber and the glass or the rubber and the car body. The glazing sealant is used for spotting for sealing overlaps, joints, folds, screwed joints and moldings between the metal bodywork, glass, plastic, wood and other materials to themselves and to each other.



Properties

- high tackiness
- odorless
- cannot be painted over
- sealant
- non-hardening
- outstanding compatibility with paint

Technical data

Base	polyisobuthylene, synthetic resin, filler, solvent
Form	pastelike, liquid
Curing / setting	emission of solvents
Specific weight	ca. 1,4 kg/l
Processing time / open time at 20 °C / 50 % rh	ca. 3 h
Solids content, 3 h at 120 °C	ca. 89 % DIN 53216
Thermal stability	-30 - +100 °C
Processing temperature	+5 - +35 °C
Chemical resistance	water, dilute acid, leaching
Color / appearance	black
Recommended storage temperature	+10 - +30 °C
Shelf life in original sealed container	36 months

Areas of application

Liqui Moly Spotting Glazing Sealant is used for providing elastic seals in car, trailer, container and caravan construction. This product is also used for sealing applications in ship building, in the metal industry and in the construction industry.

Application

The surfaces to be sealed must be clean, dry and free of grease. The glazing sealant is applied by spotting using a hand or a compressed-air cartridge gun. A pressure of around 2-3 bar must be used if applied using compressed air. Inject Spotting Glazing Sealant into the joints, ridges and gaps, etc. and, if necessary, smooth it down. After a brief flash-off time, excess material can be dabbed off using itself or an adhesive tape.

Available pack sizes

310 ml Cartridge plastic	6196 DE-EN-ES-FR-IT-NL-PT

Our information is based on thorough research and may be considered reliable, although not legally binding.

LIQUI MOLY GmbH
Jerg-Wieland-Str. 4
89081 Ulm-Lehr

Phone: +49 (0)731/1420-0
Fax: +49 (0)731/1420-82
e-mail: info@liqui-moly.de

Technical hotline: +49 (0)731/1420-871
www.liqui-moly.com