

Size Resin

Description

Clear, liquid, UV-curing adhesive for filling in surface damage during windshield repair.

Properties

- optimizes economical use
- very high standard of quality
- simple to use
- professional repairs

Technical data

Color / appearance	clear
Form	liquid
Odor	characteristic (acid)
Density at 20 °C	1,06 g/cm ³
Curing system	UV-hardening
Flash point	>93 °C
Vapor pressure at 30 °C	0,8
Hardness, Shore A	D80
Processing temperature	-30 °C
Recommended storage temperature	5 - 15 °C, protect from heat and direct sunlight, tightly re-seal container immediately after each use.
missing translation	9 Monate



Our information is based on thorough research and may be considered reliable, although not legally binding.

Areas of application

For sealing the surface of stone cracks in laminate glass car windows after repairs.

Application

Add a drop of Size Resin to a Mylar square and position this over the impact point. As an alternative, add a drop of Size Resin directly to the impact point and cover it with a Mylar square. Use a UV lamp with an output of 4 to 10 watts for curing. This is included in our case for laminated glass repair part no. 6261 or 6265. After the Size Resin cures, the surface can be leveled using a razor blade, also included in the case for laminated glass repair, and then polished with Polishing Paste part no. 6297. This enables the best possible repair result.

Note: The product should not come into contact with rubber or plastic parts or painted surfaces of the vehicle. In the event of contact, immediately rinse thoroughly with plenty of water or glass cleaner.

Available pack sizes

5 ml Bag plastic 6298
D